



# FlameOFF® Fire Barrier Paint

## Submittal Data Sheet Gypsum/Wood

### Selection & Specification Data

Generic Type	A water-based intumescent coating that consists of a vinyl acetate resin.
Description	A decorative, thin-film intumescent coating designed for fire protection of Gypsum and Wood applications for interior use requiring ASTM E119, ASTM E84, NFPA 251, ULC CAN S-101.
Features	<ul style="list-style-type: none"> <li>Certified to ASTM E119/UL 263</li> <li>Decorative aesthetic coating - provides a hard, durable, architectural finish.</li> <li>Well suited for residential and commercial applications</li> <li>Space saving- ideal for applications when additional layers of gypsum cannot be installed</li> <li>Compatible with most topcoats (though not required)</li> <li>Thin film coating - offers an economical solution to alternative fireproofing</li> <li>low VOC, LEED compliant</li> <li>Easy repair - If damaged, product can be patched easily</li> </ul>
Color	White
Finish	Smooth
Primer	Wood: Recommended but not required Gypsum: Not required *Some tape/mud/putty products will better receive intumescent paint if first primed.
Topcoat	For interior conditioned space, topcoating is not required but may be applied for aesthetic purposes.  Product must be topcoated if there are environmental exposure requirements. Refer to FlameOFF® Coatings, Inc. technical support.  Intumescent coating must be applied to the required DFT and fully cured before topcoat is applied.
Thickness Per Coat	Recommended 20-35 Mils WFT *Range: 15-45 Mils WFT. Maximum thickness per coat depends upon applicator experience, substrate, and job site conditions.
Solids Content	By Volume 71%
Theoretical Coverage Rates	1075 sq ft/gallon at 1 mil (1002 m / at 25 microns) 36 sq ft/gallon at 30 mils (3.3 2 m / at 750 microns)
VOC Values	As Supplied 0.06 lbs/gal (7 g/l)

### Testing / Certification

Listing	This product is ICC-ES Listed and UL Classified. It has been tested in accordance with ASTM E119/UL 263 Fire Endurance requirements to meet the full scale requirement of IBC/NFPA Building Codes.
---------	--



\*See ICC  
ESL 1191, ESL1192



\*See UL Fire Resistance  
Directory R38327

Contact FlameOFF® Coatings for any additional testing outside listing reports provided above

### Required DFT

Substrate**			
Required Dry Film Thickness & Corresponding Coverage Rate	5/8" Type X Gypsum	1/2" Regular Gypsum	Wood
Class A*	15 Mils DFT 75 sq ft/gal	15 Mils DFT 75 sq ft/gal	10 Mils DFT 110 sq ft/gal
Class A, 30 min extended*	15 mils DFT 75 sq ft/gal	X	20 mils DFT 56 sq ft/gal
1 hour*	30 Mils DFT 37 sq ft/gal	30 Mils DFT 37 sq ft/gal	30 Mils DFT 37 sq ft/gal
2 hour*	45 Mils DFT 25 sq ft/gal	X	X

\* ASTM E84 Class A, E2768 30min extended Class A, and E119 1 & 2 hour ratings.

\*\* Substrates listed are part of a tested assembly and are not considered rateable in all conditions. Contact our technical team with any specific questions.

### Packaging, Handling & Storage

Shelf Life	12 Months Shelf life when kept at recommended storage conditions and in original unopened containers.
Shipping Weight	64 lbs per 5 gal pail
Storage	Store indoors in a dry environment between 45°F and 105°F (7°C and 40°C)
Packaging	5 Gal This product is proudly manufactured in the USA

Email: [info@flameoffcoatings.com](mailto:info@flameoffcoatings.com)

FlameOFF® Coatings, Inc. owns and certifies all data in this document. This document may not be altered by anyone other than FlameOFF® Coatings, Inc.

The data and suggested formulations in this bulletin are based on information believed to be reliable and are offered solely for evaluation, investigation and verification of numerous factors affecting results. FlameOFF® Coatings, Inc. products are sold with the understanding the purchasers will make their own tests to determine the suitability of these products for the particular use. We assume no liability or responsibility for any damage to person or property resulting from or incident to the use of our products. Statements concerning the use of FlameOFF® Coatings, Inc. products are not be construed as recommending the infringement of any patent, and no liability for infringement arising out of any such use is assumed.

Web: [www.flameoffcoatings.com](http://www.flameoffcoatings.com)

Revised 02/01/24





# FlameOFF® Fire Barrier Paint

## Submittal Data Sheet Gypsum/Wood

### Substrate & Surrounding Surface Preparation

<b>General</b>	All surfaces must be primed and must be clean, dry, and free of oil, grease, loose scale, dirt, dust or other materials that would impair the bonding of the intumescent coating to the substrate.
<b>Overspray</b>	As with all spray-applied coatings, care should be taken to mask off areas not intended to be rated by the intumescent paint. All adjacent and finished surfaces should be protected from damage and overspray.

### Application Conditions and Curing Schedule

Application Temperature & Humidity	Condition		Material	Humidity	
	Minimum	45°F (10°C)	0%	Maximum	100°F (40°C)

Surface Temp. & 50% Relative Humidity	Handle	Recoat (spray)	Recoat (brush)	Topcoat
70 °F (21 °C)	24 Hours	7-8 hours	2-3 hours	48-72 hours

\*Curing times are dependent upon temperature, ventilation, and humidity. Lower temperatures will slow down the curing process, higher temperatures will speed up the curing process. Additional ventilation (add fan) may expedite curing process. For optimum curing, it is recommended to apply coats at 20-45 mils wet per coat. **Material is ready to be topcoated when an average Shore D hardness of 70 is achieved.**

**Product application Guide should be reviewed in its entirety prior to application of Fire Barrier Paint.**

### Application Equipment Guidelines

General equipment guidelines are given below, and may need to be modified depending on individual jobsite conditions in order to achieve the desired results. See Application Guide for full application details. Contact FlameOFF® Coatings with any questions.

<b>Airless Spray</b>	Use 1.0 gal. per minute electric airless (minimum) to provide an operating pressure of 3,000 p.s.i. (140 kg/cm <sup>2</sup> ). ** Remove rock catcher from siphon tube.**
<b>Spray Gun</b>	Contractor Gun (with filter removed) or equivalent
<b>Spray Tips</b>	0.021" - 0.025"
<b>Fan Size</b>	4"-10" (depending on section being sprayed)
<b>Hose Length</b>	50' (15 m) maximum

### Mixing & Thinning

<b>Thinning</b>	DO NOT THIN or alter in any way.
<b>Mixer</b>	Use 1/2" electric or air driven drill with a slotted paddle mixer (300 rpm under load)
<b>Mixing</b>	Product must be mixed using a 1/2" electric air driven drill with a slotted paddle or Jiffy mixer blade. Mix material for a minimum of 5 minutes to achieve the necessary texture required before spraying.

### Application Procedures

<b>General</b>	Product may be applied by brush or spray application. Do not apply with a roller. Spray application is recommended for the optimum appearance.
<b>Airless Spray</b>	A single coat built up with a number of quick passes allows greater control over quantities, thickness and finish. **Note - In most conditions, it is advantageous to apply two thin coats rather than one thick coat.**
<b>Application Rates</b>	Spray: 20-45 Mils Wet Film Thickness Brush: 10 Mils Wet Film Thickness
<b>Wet Film Thickness</b>	Frequent thickness measurements with a wet film gauge are recommended during the application process to ensure uniform thickness.

### Cleanup & Safety

<b>Cleanup</b>	Flush pump, gun, tips, hoses and mixer with hot water at least once per day.
<b>Safety</b>	Follow all safety precautions on the product Material Safety Data Sheet. This product is water based and non hazardous. Appropriate PPE is recommended during application.

### Maintenance

<b>General</b>	If coating becomes damaged, rebuild the required thickness by spray or brush. When dry, smooth and finished, topcoat may be applied. The repair area must follow all surface preparation requirements before reapplying the coating. The coating must be built back to the original thickness.
----------------	--

Email: [info@flameoffcoatings.com](mailto:info@flameoffcoatings.com)

FlameOFF® Coatings, Inc. owns and certifies all data in this document. This document may not be altered by anyone other than FlameOFF® Coatings, Inc.

Web: [www.flameoffcoatings.com](http://www.flameoffcoatings.com)



*The data and suggested formulations in this bulletin are based on information believed to be reliable and are offered solely for evaluation, investigation and verification of numerous factors affecting results. FlameOFF® Coatings, Inc. products are sold with the understanding the purchasers will make their own tests to determine the suitability of these products for the particular use. We assume no liability or responsibility for any damage to person or property resulting from or incident to the use of our products. Statements concerning the use of FlameOFF® Coatings, Inc. products are not be construed as recommending the infringement of any patent, and no liability for infringement arising out of any such use is assumed.*

Revised 02/01/24