



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

June 19, 2024

FLAMEOFF COATINGS
3915 Beryl Rd. Suite 130
Raleigh, NC 27607

Reference: Laboratory Test Report
Lab Identification No. 60172
Invoice No. 91519

Dear Sir or Madam:

One (1) carpet sample, identified as **Product: FlameOFF FR Clear**, was received and tested in accordance with ASTM D2859, "Standard Test Method for Ignition Characteristics of Finished Textile Floor Cover Materials. **Per your request, the sample was tested after ten (10) laundering cycles at 140F (Tumble Dry).** The results are as follows:

Test Results

<u>Specimen No.</u>	<u>Uncharred Area (in.)</u>
1	3.2
2	3.3
3	3.1
4	3.5
5	3.2
6	3.4
7	3.6
8	3.1

The sample submitted **meets** the minimum requirements of the above standard. If the charred area does not extend to within one (1) inch of the edge of the hole in the flattening frame at any point for at least seven of the eight specimens, the rug meets the acceptance criterion.

Sincerely,

Brian S. Dement

BSD/mr

