



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

May 17, 2021

Mr. James Turner
FLAMEOFF COATINGS, INC.
1110 Navaho Drive
Suite 110
Raleigh, NC 27609

Reference: Laboratory Test Report
Lab Identification No. 45661
Invoice No. 76969

Dear Mr. Turner:

One (1) fabric sample, identified as **FlameOff FR Clear Woven Cotton**, was received and tested in accordance with the California Administrative Code Title 19--Public Safety, Section 1237.1 Flame Resistance, Small Scale Test. The results are as follows:

Test Results

<u>Specimen Number</u>	<u>After Flame (sec)</u>		<u>Char Length (in)</u>	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	0.0	0.0	2.8	2.6
2	0.0	0.0	1.8	3.3
3	0.0	0.0	3.4	3.0
4	0.0	0.0	3.4	3.3
5	0.0	0.0	3.4	2.5
Avg.	0.0	0.0		

The sample submitted, in its original state, **meets** the minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

