



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

May 17, 2021

Mr. James Turner
FLAMEOFF COATINGS, INC.
1110 Navaho Drive
Suite 110
Raleigh, NC 27609

Reference: Laboratory Test Report
Lab Identification No. 45661
Invoice No. 76969

Dear Mr. Turner:

One (1) fabric sample, identified as **FlameOff FR Clear Woven Cotton**, was received and tested in accordance with ASTM D 6413-15, “Standard Test Method for Flame Resistance of Textiles (Vertical Test)”. The results are as follows:

TEST RESULTS

<u>Specimen Number</u>	<u>After Flame (seconds)</u>		<u>After Glow (seconds)</u>		<u>Char Length (inches)</u>	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	0.0	0.0	0.0	0.0	2.5	3.6
2	0.0	0.0	0.0	0.0	3.2	4.0
3	0.0	0.0	0.0	0.0	2.6	4.0
4	0.0	0.0	0.0	0.0	3.8	2.9
5	0.0	0.0	0.0	0.0	3.9	3.1
Avg	0.0	0.0	0.0	0.0	3.2	3.5

Note: There were no occurrences of melting or drippings.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

