



336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

May 17, 2021

Mr. James Turner
FLAMEOFF COATINGS, INC.
1110 Navaho Drive
Suite 110
Raleigh, NC 27609

Reference: Laboratory Test Report
Lab Identification No. 45661
Invoice No. 76969

Dear Mr. Turner:

One (1) fabric sample, identified as **FlameOff FR Clear Woven Cotton**, was received and tested in accordance with CAN/ULC-S109-14, "Standard for Flame Tests of Flame-Resistant Fabrics and Films", Large-Flame Test. The results are as follows:

Test Results

| <u>Specimen Number</u> | <u>Residual Flame (Seconds)</u> | <u>Char Length (Millimeters)</u> |
|------------------------|---------------------------------|----------------------------------|
| Length 1 | 0.0 | 114 |
| Length 2 | 0.0 | 305 |
| Width 1 | 0.0 | 330 |
| Width 2 | 0.0 | 152 |

The fabric sample submitted **meets** the minimum requirements of the Large-Flame Test. The length of char on the individual folded specimens shall not exceed 635 millimeters. No residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

