



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

May 17, 2021

Mr. James Turner
FLAMEOFF COATINGS, INC.
1110 Navaho Drive
Suite 110
Raleigh, NC 27609

Reference: Laboratory Test Report
Lab Identification No. 45661
Invoice No. 76969

Dear Mr. Turner:

One (1) fabric sample, identified as **FlameOff FR Clear Woven Cotton**, was received and tested in accordance with the National Fire Prevention Association No. 705, "Recommended Practice for a Field Flame Test for Textiles and Films, 2018 Edition". The results are as follows:

Test Results

<u>Afterflame</u> <u>(Seconds)</u>	<u>Residual</u> <u>(Seconds)</u>	<u>Flaming Length</u> <u>(Inches)</u>
0.0	0.0	0.7

The sample submitted **meets** the minimum requirements of the above standard. There should be no more than 2.0 seconds of afterflame for any individual specimen. Materials that break or drip flaming particles should be rejected if the materials continue to burn after they reach the floor. During the exposure, flaming should not spread over the complete length of the sample or, in the case of larger samples, in excess of 4 inches from the bottom of the sample.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

